

# Defthane® Polyurethane

## *Indoor/Outdoor Platinum Protection for hard-use wood surfaces.*

Defthane® Polyurethane gives professional results on any wood surface. It is the heavy-duty choice for sealing and finishing INTERIOR and EXTERIOR wood, metal or marine (above waterline) surfaces.

### **Quick & Easy.**

- Goes on smooth with a brush, pad or roller.
- Apply over old finish (read label instructions).
- Easy to touch-up.

### **Proven Durability.**

- Tough finish outlasts varnish 3 to 1.
- Enhances finished or unfinished wood.
- Resists abrasion, marring, alcohol and other common household chemicals.
- Used on the R.M.S. Queen Mary for over 25 years.

### **Protects Interior/Exterior Hard-Use Areas.**

- Floors
- Doors
- Furniture
- Cabinets
- Metal
- Great for use as an "above waterline" marine spar finish

Note: Defthane Polyurethane ambers over light colored surfaces.

### **Finishes & Sizes.**

- Available in three finishes: Gloss, Semi-Gloss and Satin.
- Sizes include: Pint, Quart, Gallon, 5-Gallon, Drum and Aerosol.
- Also offered in VOC Compliant Formulas for SCAQMD and OTC.

### **Convenient Aerosol Cans.**

- Ideal for small projects, quick touch-ups or hard-to-reach areas.
- Patented Fanspray™ nozzle rotates to create a more precise vertical or horizontal fan spray pattern; allows for better control, less overspray and more even coverage.



**APPLICATION:** Wear rubber gloves while working with any stain or finish product. If staining, note dry time on stain label before finishing.

#### **FINISHING UNFINISHED INTERIOR/EXTERIOR WOOD:**

1. Sand wood and wipe off dust.
2. Apply first coat with long, smooth strokes. Let dry for 4-6 hours (450 VOC) or 6-8 hours (275 VOC).
3. Sand smooth, remove dust.
4. Apply 2 more thin coats. Where exposure or wear is severe, apply additional coats. Let dry 4-6 hours between coats (450 VOC) or 6-8 hours between coats (275 VOC).
5. Use paint thinner (mineral spirits) for clean up.
6. Sand and repeat when first signs of deterioration appear.



Tel: (800) 458-3338  
Fax: (330) 821-8019  
Email: AskDeft@deftfinishes.com  
Web Site: [www.deftfinishes.com/trade](http://www.deftfinishes.com/trade)